

**PRODUCT DATA SHEET**

<b>Product</b>	<b>Wood Bleach</b>
<b>Type</b>	Two pack bleaching kit for wood based on stabilised Hydrogen Peroxide.
<b>Intended Use</b>	For use on bare wood to make it white or lighter in colour.
<b>Special Features</b>	Removes weather stains and discolourations.
<b>Preparation</b>	Will only work on bare wood. All varnish, lacquer or polish must be removed before applying the solutions. Old finishes are best removed with <b>Rustin's Strypit Paint and Varnish Stripper</b> . Remove as much of the old finish as possible with a scraper, then damp the surface again with Strypit and rub with the grain with NO 1 or 2 steel wool. Wipe surface with clean rag and allow to dry.
<b>Application</b>	Apply solution "A" to clean, dry wood with a brush and leave for 10-20 minutes before applying the "B" solution. Some woods will darken when "A" solution is applied. The actual bleaching takes place after application of "B" solution.
<b>Coats</b>	One coat of "A" solution followed by a coat of "B" solution.
<b>Drying Time</b>	After application of "B" solution leave for a minimum of 2 hours. If the product dries out it can form crystals which can be very difficult to remove so ensure sufficient solution is applied to prevent drying out.
<b>Re-coating Time</b>	If the wood is very dark or badly stained, repeat application of both solutions after 2 hours.
<b>Application Temp.</b>	Do not use in extreme temperatures.
<b>Coverage</b>	One Bleaching Kit(500 ml x 2) will bleach approx. 11 sq metres depending on absorbency of wood.
<b>Maintenance</b>	N/A
<b>Compatibility</b>	After bleaching <b>Rustin's Wood Dye</b> may be applied followed by any of the <b>Rustins varnishes or oils</b> to seal the wood. For oil based and polyurethane varnishes, French Polish or wax finishes after bleaching the surface must be washed with a solution of Acetic acid (white vinegar), 1 teaspoon in a cup of water. Apply liberally and allow to dry. If <b>Rustin's Plastic Coating</b> is to be applied after bleaching, wash the surface with a solution of spirits and salts (hydrochloric acid), 1 part to 7 parts water. Apply liberally and allow to dry. If a white deposit is still evident repeat this process. If <b>Rustins Quick Dry Varnish</b> is used do not use white vinegar or spirits of salt but wash thoroughly with water and allow to dry before coating.
<b>Settlement</b>	N/A
<b>Shelf-life/Storage</b>	Store in a cool dark place, away from sunlight.
<b>Hazards</b>	Solution "A"; Irritant. Solution "B"; Corrosive, Oxidising. Wear suitable eye/face protection. A full Health and Safety Data Sheet is available on request or on <a href="http://www.rustins.co.uk">www.rustins.co.uk</a>
<b>Clean-Up</b>	Clean all equipment with water.

**Sizes**

Set A&amp;B, Approx 500ml each solution